



Cross-Linked Shrink Film - CX

TYPICAL PROPERTIES

Gauge			45	60	75	100
	Unit	Test Method				
Yield	Sq. in. per pound		66,000	50,000	40,000	30,000
Tensile properties:			MD TD	MD TD	MD TD	MD TD
Tensile strength	N/mm ²	D-883	125 115	120 100	125 105	110 100
Elongation	%	D-884	105 100	105 100	110 107	120 115
Seal Strength	N/mm ²	Int. meth.	71	67	65	60
Tear propagation	gr	D-1922	7.3	10	11.5	13
Cof. film-film, kinetic	adim.	D-1894	0.26	0.25	0.25	0.25
Shrink at 250°F	%	D-2732	MD TD 70 71	MD TD 68 69	MD TD 67 67	MD TD 66 66
Optical properties:						
Haze	%	D-1003	1.5	1.7	2	2.4
Gloss	photoc.	D-2457	131	125	123	121